

PCT

WORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification 6: B23K 13/02, 9/00		A1	(11) International Publication Number: WO 99/08827
			(43) International Publication Date: 25 February 1999 (25.02.99)
(21) International Application Number: PCT/EP98/05474		(81) Designated States: AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GE, GH, GM, HR, HU, ID, IL, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, UA, UG, US, UZ, VN, YU, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).	
(22) International Filing Date: 19 August 1998 (19.08.98)			
(30) Priority Data: 9717440.3 19 August 1997 (19.08.97) GB 9805661.7 17 March 1998 (17.03.98) GB			
(71) Applicant (for all designated States except US): SHELL INTERNATIONALE RESEARCH MAATSCHAPPIJ B.V. [NL/NL]; Carel van Bylandtlaan 30, NL-2596 HR The Hague (NL).			
(72) Inventors; and (75) Inventors/Applicants (for US only): PIETRAS, Bernd-Georg [DE/DE]; Sandriedeweg 12, D-30900 Wedemark (DE). JAHN, Michael [DE/DE]; Am Kohlerort 12, D-29313 Hambühren (DE).			
(74) Agent: SHELL INTERNATIONALE RESEARCH MAATSCHAPPIJ B.V.; P.O. Box 302, NL-2501 CH The Hague (NL).			

Published


With international search report.

Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.

(54) Title: APPARATUS FOR AMORPHOUS BONDING OF TUBULARS

(57) Abstract

An apparatus for amorphous bonding of tubulars (110, 111) comprises a double skin jacket (2, 113, 114) which can be placed around said tubulars (110, 111), which skins define a sealed inner fluid space (11, 121) which contains shield gas and a heating element (1, 129) and a sealed outer fluid space (9, 119) surrounding the inner fluid space (11, 121) to reduce the risk of explosion during the amorphous bonding process.



FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakhstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

- 1 -

APPARATUS FOR AMORPHOUS BONDING OF TUBULARS

Background of the invention

This invention relates to an apparatus for amorphous bonding of tubulars.

5 During the construction of oil and gas wells it is usual to connect a large number of tubulars. Conventionally this is effected by screw couplings. One of the disadvantages of this construction is that the couplings are prone to corrosion with the result that a whole string of tubulars may have to be replaced every
10 few years, particularly in high temperature, high pressure wells containing corrosive vapours.

It has been suggested that the longevity of such tubulars could be greatly increased, perhaps up to 25 years, if the couplings could be dispensed with.

15 One proposal for dealing with this problem has been to weld tubulars together. However, this is extremely hazardous at the head of an oil or gas well. Furthermore, normal manual welding does not result in a homogeneous metallurgical structure and the corrosion problem
20 remains.

A technique of joining metal components known as "amorphous bonding" has been successfully utilised in the automotive industry. The surfaces of the components to be joined are ground into parallism. A foil of a metal alloy
25 is then placed between the components which are mechanically pressed together. The joint is then subjected to local heating by an induction heater. The resulting structure is nearly metallurgically homogeneous.

It will be appreciated that it would be extremely desirable to be able to join tubulars by amorphous bonding. However, the technical difficulties are daunting insofar as it is necessary to transfer a process

suited to a precision engineering shop to an area where inflammable and often explosive gas mixtures are present and where the rigidity of an engineering shop floor is replaced by a drilling platform which may well be offshore and which may be in continuous motion in heavy seas and inclement weather.

It is observed that UK patent specification No. 540,519 discloses a welding device comprising a ring burner which is surrounded by an annular water cooling jacket to reduce explosion hazards during the welding process.

European patent application No. 157131 discloses a double chambered sealing system for welding pipe end which injects inert shield gas in radial and axial directions into unsealed areas around the welding zone to prevent air contamination of said zone.

European patent application No. 418606 discloses an amorphous bonding apparatus in which nitrogen shield gas is injected into a jacket surrounding the bonded tubular ends and also nitrogen gas is injected into the interior of the bonded tubulars to create a virtually oxygen free atmosphere in the region of the bond.

Although the known devices provide some protection against explosion hazards they do not provide sufficient protection in an hazardous environment at the head of an oil or gas well.

The present invention is primarily concerned with reducing the risk of explosion while the amorphous bonding is taking place.

Summary of the Invention

According to the present invention there is provided an apparatus for amorphous bonding the ends of tubulars which are in substantial axial alignment and surrounded by a shield gas, said apparatus comprising a jacket which in use is placed around said adjacent tubular ends, said jacket having an inner skin which, in use, defines a sealed inner fluid space containing a heating element and

shield gas, and an outer skin which surrounds the inner skin such that in use a sealed outer fluid space is defined between said inner and outer skin.

5 It is preferred that said jacket is formed by two parts which are slidably mounted on a support frame and which can be urged together to form said jacket and that the inner skin is provided with fluid communication means which allow in use fluid to flow in a controlled manner from the inner fluid space into the outer fluid space or vice versa.

10 In one embodiment the apparatus comprises means to introduce a shield gas into the inner fluid space and means to introduce water into the outer fluid space and the fluid communication means comprises a conduit which, 15 in use, can convey said shield gas to within said outer fluid space at a selected depth between the water level in the outer fluid space so that a selected pressure difference is maintained between the inner and outer fluid spaces.

20 In an alternative embodiment the apparatus comprises an inlet pipe for introducing a shield gas into the outer fluid space, an orifice in the inner skin for allowing the shield gas to flow from the outer fluid space into the inner fluid space and an outlet pipe for allowing the shield gas out of the inner fluid space, wherein 25 preferably pressure control means are provided which in use control the pressure in the inner and outer fluid space such that the pressure in the inner fluid space is higher than the ambient pressure and the pressure in the outer fluid space is higher than in the inner fluid 30 space. In this manner a high pressure gas shield is created in the outer fluid space which prevents air to flow into the inner fluid space and hot shield gases to leak from the inner fluid space into the atmosphere.

35 Suitably the apparatus further comprises a packer which in use is inserted into the interior of the tubular ends that are bonded by the apparatus, which packer

comprises an elongate mandrel having a resilient packer element adjacent each end thereof, means to enable an inert shield gas to be introduced into an end of said elongate mandrel and to leave said elongate mandrel between said resilient packer elements, and means to enable water to be introduced into said end of said elongate mandrel and to leave said elongate mandrel between said resilient packer elements.

It will be understood that the external double skin jacket and the internal packer provide an adequate protection against explosion hazards during the amorphous bonding process since they prevent explosive gases to reach the area of the heating element and the tubular ends heated thereby and also prevent hot shield gases or other fluids to escape into the surrounding atmosphere.

Brief description of the drawings

For a better understanding of the present invention reference will now be made, by way of example, to the accompanying drawings, in which:-

Fig. 1 is a vertical section through an amorphous apparatus according to the present invention;

Fig. 2 shows, to an enlarged scale, a view on line II-II of Fig. 1; and

Fig. 3 shows a schematic cross-sectional view of an apparatus according to the present invention in which pressurized shield gas is injected via the outer fluid space into the inner fluid space and then vented into the atmosphere.

Detailed description of the invention

Referring to Fig. 1 there is shown an amorphous bonding apparatus which is generally identified by reference numeral 101.

The amorphous bonding apparatus 101 comprises a support frame 102 which is provided with wheels 103 which run in channels (not shown).

Two clamps 104 and 105 are disposed towards the bottom of the support frame 102 whilst another two clamps

106 and 107 are mounted near the top of the support frame 102 and can be displaced vertically by two piston-and-cylinder assemblies 108 and 109.

5 In use, a lower tubular 110 is secured in slips (not shown). The support frame 102 is then advanced towards the lower tubular 110 and the clamps 104 and 105 secured thereto.

10 An upper tubular 111 is then manoeuvred into position using an elevator or a positioning device and gripped in the clamps 106 and 107. The piston-and- cylinder assemblies 108 and 109 are then actuated to bring the lower end of the upper tubular 111 into close proximity to the upper end of the lower tubular 110. The adjacent ends of the upper and lower tubulars are then brought
15 into substantial alignment and machined such that the adjacent ends are substantially flat and parallel to each other.

20 Then a foil of alloy is placed on the upper surface of the lower tubular 110 and the upper tubular 111 is urged downwardly by the piston and cylinder assemblies 108, 109 with a predetermined pressure which varies according to the composition of the tubulars and the composition of the foil.

25 At this point the sealable heating apparatus 112 is mounted on the tubulars straddling the foil. The sealable heating apparatus 112 comprises two halves 113 and 114 which can be advanced and retracted by hydraulic rams. In particular, the half 112 can be advanced and retracted by hydraulic rams 115 whilst the half 113 can be advanced
30 and retracted by hydraulic rams 116.

As can be seen from Fig. 2 the half 113 comprises an inner skin 117 and an outer skin 118 which define an outer fluid space 119 therebetween. The faces of the inner skin 117 and the outer skin 118 are each provided
35 with resilient seals 120 which engage on sealing surfaces on the half 114 and together define a jacket which surrounds the lower tubular 110 and the upper tubular

111. The resilient seals 120 also extend around the lower tubular 110 and the upper tubular 111 respectively. As indicated above, after the ends of the lower tubular 110 and the upper tubular 111 have been prepared for bonding
5 a film of a suitable alloy is placed therebetween and the upper tubular 111 pressed against the lower tubular 110.

The halves 113 and 114 are then moved into position either side of the tubulars 110, 111 and pressed together with the hydraulic rams so as to form an inner chamber
10 121 enclosed by the inner skin 117. The two halves 113 and 114 are then fastened together with six mechanical fasteners (not visible) to ensure that the halves do not inadvertently come apart.

The outer fluid space 119 is then filled with water
15 (H₂O) from inlet pipe 122. The water fills the outer fluid space 119 and leaves through outlet pipe 123. The water is continually pumped through the outer fluid space 119 and its presence is detected by a sensor 124 which is designed to inhibit the remainder of the process if no
20 water is present or the temperature of the water exceeds a predetermined temperature.

The outer fluid space 119 can be emptied via drain line 125. An emergency water tank 126 and emerging water supply 127 are provided so that the outer fluid space 119
25 can be deluged with water in an emergency, for example catastrophic failure of a seal resulting in loss of water from the outer fluid space 119.

The inner fluid space or chamber 121 is cooled by a flow of shield gas which is introduced through a manifold
30 128 situated below an induction heating ring 129. The shield gas is supplied via gas supply pipe 130 which is, in turn, connected to a source of compressed air via air line 131 and a source of argon shield gas via argon line 132.

35 The inner chamber 121 is also provided with two gas exit pipes 133, 134 which are connected to an exit manifold 135. The exit manifold 135 is connected to an

argon flushing line 136 and a line 153 which opens into the outer fluid space 119 well below outlet pipe 123.

A sampling pipe 137 is provided to allow samples of gas from within the inner chamber 121 to be continually taken and analysed.

The induction heating ring 129 is independently water (H₂O) cooled by a water supply which is pumped through inlet pipe 138 and leaves through outlet pipe 139. The induction heating ring 129 is provided with power via heavy metal conduits which are symbolised by wires 140 and 141.

While the heating apparatus 112 is being prepared an internal packer 142 is lowered down the upper tubular 111. The purpose of the internal packer 142 is threefold, viz:-

- (1) to prevent inflammable, and possibly explosive, vapour rising up the lower tubular 110;
- (2) prevent air coming down the upper tubular 111; and
- (3) allow a desired atmosphere to be created in the vicinity of the joint.

With these purposes in mind the internal packer 142 comprises an elongate mandrel 143 with a resilient packer element 144, 145 at each end thereof. Each resilient packer element 144, 145 is connected to a source of pressurized water via packer element control line 146. When pressurized water is supplied through packer element control line 146 both the packer elements 144, 145 expand and form a seal between the elongate mandrel 143 and the upper tubular 111 and lower tubular 110 respectively thereby forming an isolated chamber 147.

The centre of the elongate mandrel 143 is provided with an elongate bore 148 which is connected to a water (H₂O) inlet tube 149 and is provided with a multiplicity of radial outlet tubes 150 which open into the isolated chamber 147. An argon supply pipe 151 also passes downwardly through the elongate mandrel 143 and opens into

the isolated chamber 147 immediately above the resilient packer element 145.

After the apparatus 112 has been properly positioned, the internal packer 142 positioned, and the resilient packer elements 144, 145 set, the amorphous bonding process proceeds as follows:-

1. Water flow is established through the outer fluid space 119.
2. The inner chamber 121 is purged with air for a fixed time and in any event until the gas sampled through the safety device 137 does not record an unacceptable level of hydrocarbons.
3. The air supply is switched off and argon is passed through the inner chamber 121 to form an atmosphere of argon shield gas to the outside of the joint.
4. When the sample of gas being taken through the sampling pipe 137 indicates that the atmosphere in the inner chamber 121 is substantially pure argon the inner chamber 121 is ready. During steps 3 and 4 argon leaves the system via argon flushing line 136 and can, if desired, be recovered for use in other application.
5. During steps 2, 3 and 4 the isolated chamber 147 is purged by the introduction of argon shield gas through argon supply pipe 151. The argon purges the isolated chamber 147 and leaves via an outlet tube (not visible). A sensor in the outlet tube checks the argon content of the gas passing through the outlet tube and inhibits activation of the induction heating ring 129 until the gas passing through the outlet tube is substantially pure argon. Air is also introduced into the upper tubular 111 via pipe 152 to purge any combustible gases from inside the upper tubular.
6. At this stage power is applied to the induction heating ring 129 to heat the metal in the area of the joint to a temperature in the range of about 1000-1300°C for a predetermined period. However, safety requirements necessitate the surrounding area being kept

as cool as practicable. With this in mind argon is pumped through the inner chamber 121 and the isolated chamber 147 throughout the heating process. Furthermore, air is pumped through the pipe 152.

5 The argon which leaves the inner chamber 121 via gas exit pipes 133, 134 is directed through line 153 by closing valves 154 and opening 155. The argon bubbles through the water and is cooled thereby before venting into the atmosphere. Furthermore, the pressure of argon
10 in the inner chamber 121 can be controlled by varying the depth of the outlet of the line 153 below the water level. This provides a simple and effective method of controlling the pressure in the inner chamber 121.

15 After the requisite period the induction heating is ceased and the joint allowed to cool whilst the flow of argon continues.

20 When the joint has been cooled sufficiently the supply of argon through argon supply line 151 is terminated and cooling water is introduced through water inlet tube 149. The supply of water is continued until the tubulars 110 and 111 are suitably cooled at which time the supply of argon to the inner chamber 121 via gas supply pipe 130 is stopped. The supply of water to the outer fluid space 119 is also stopped and the outer fluid
25 space 119 drained by opening a valve 156 in the drain line 125.

 The halves 113 and 114 are then withdrawn.

30 Only when it is determined that it is safe to do so is the water supply to the packer 142 via water inlet pipe 149 terminated. The resilient packer elements 144, 145 are then deflated and the packer 142 withdrawn.

 The tubulars 110 are then released from the clamps 104, 105 106, 107 and the amorphous bonding apparatus 101 rolled back.

35 The joint is then tested. If the test is successful the tubulars are lifted to enable the slips to be re-

- 10 -

leased and lowered into the hole. The slips are then applied and the process repeated.

5 Various modifications to the embodiment described are envisaged, for example air, or preferably, as described with reference to Fig. 3, an inert shield gas such as nitrogen could be circulated through the outer fluid space 119 instead of water. Instead of purging the isolated space 147 with argon it could be initially purged with air subsequently argon for the heating step. 10 If desired, after the induction heating is completed and cooling has commenced the resilient packer element 144 (but not the resilient packer element 145) could be released prior to the introduction of cooling water. This would allow any steam found to rapidly escape and further 15 purge the inside of the upper tubular.

Turning now to Fig. 3 an amorphous bonding heating coil is identified by reference numeral 1.

20 The amorphous bonding heating coil 1 surrounds a tubular 110 and is surrounded by a jacket enclosure 2 having a first half 3 and a second half 4.

Each half 3, 4 comprises an inner skin 7 and an outer skin 8 defining an annular outer space 9 therebetween. The halves 3 and 4 are provided with seals which interengage when the halves 3 and 4 are clamped together and which are intended to form the sealed jacket 25 enclosure 2. However, to facilitate understanding the present invention it will be assumed that there is a small gap 5 between the halves 3, 4.

30 In use, an inlet pipe 6 conveys inert shield gas into the annular outer space 9 between the inner skin 7 and the outer skin 8. The annular outer fluid space 9 is maintained at a pressure P_1 which is slightly greater than the ambient pressure P_0 . An orifice 10 allows part of the inert shield gas to pass into an inner fluid space 11 inside the inner skin 7. The inert gas can then pass 35 from the inner fluid space 11 to an isolated outlet

- 11 -

pipe 12 via an orifice 13 which is set to maintain the pressure P2 in the chamber 11 between P1 and P0.

5 In use, cool inert gas is passed through inlet pipe 6. Part of the cool inert gas passes into the annular outer fluid space 9 whilst the balance flows through the inner fluid space 11 via orifice 10 and orifice 13. When the induction heater 1 is operational the inert gas in the inner fluid space 11 is heated and the heated inert gas leaves via insulated outlet pipe 12
10 which vents to atmosphere in a safe area optionally after being indirectly cooled.

As can be seen from the arrows 14, 15 in the event of a leak in the outer skin 8 cool inert gas from the annular outer fluid space 9 passes through the gap into
15 the ambient air since the pressure P1 in the space 9 is higher than the ambient pressure P0. Similarly, in the event of a leak in the inner skin 7 cool inert gas passes from space 9 through the inner skin 7 into the inner fluid space 11.

20 It will be appreciated that with the arrangement disclosed the probability of hot shield gases leaking to the atmosphere surrounding the enclosure 2 is small.

Various modifications to the embodiment claimed are envisaged, for example the inlet pipe 6 and the
25 orifice 10 could be disposed to help ensure that the annular outer fluid space 9 is constantly replenished with cool inert gas, thus reducing the possibility of small pockets of hot inert gas accumulating in the outer fluid space 9. If desired several inlet pipes 6 and
30 several orifices 10 could be provided.

It will be appreciated that the orifices 10 and 13 could be formed by adjustable valves or pressure relief valves.

35 If desired flow and temperature sensors may be provided which are arranged to stop the amorphous bonding process and drench the entire area with water if a signal is detected indicative of a major leak.

- 12 -

Such sensors could comprise flow sensors in the inlet pipe 6 and the insulated outlet pipe 12.

- 13 -

C L A I M S


1. An apparatus for amorphous bonding the ends of tubulars (110, 111) which are in substantial axial alignment and surrounded by shield gas, said apparatus comprising a jacket (2, 113, 114) which in use is placed
5 around the adjacent tubular ends, said jacket (2, 113, 114) having an inner skin (7, 117) which, in use, defines a sealed inner fluid space (11, 121) containing a heating element (1, 129) and shield gas, and an outer skin (8, 118) which surrounds the inner skin (7, 117) such that in
10 use a sealed outer fluid space (9, 119) is defined between said inner and outer skin (7, 117, 9, 119).
2. An apparatus as claimed in claim 1, wherein said jacket is formed by two parts (113, 114) which are slidably mounted on a support frame (102) and which can
15 be urged together to form said jacket.
3. An apparatus as claimed in claim 1, wherein the inner skin (7, 117) is provided with fluid communication means (10, 153) which allow in use fluid to flow in a
20 controlled manner from the inner fluid space (11, 121) into the outer fluid space (9, 119) or vice versa.
4. An apparatus as claimed in claim 1, including means (131, 130, 128) to introduce shield gas into the inner fluid space (121) and means to introduce water into the
25 outer fluid space (119) and wherein the fluid communication means comprises a conduit (153) which, in use, can convey shield gas to within said outer fluid space (119) at a selected depth below the water level in the outer fluid space.
5. An apparatus as claimed in any preceding claim,
30 including a sensor (124) operative, in use, to inhibit amorphous bonding of said tubulars (110, 111) if there is insufficient water or other fluid in the outer fluid space (119).


6. An apparatus as claimed in claim 1 comprising an inlet pipe (6) for introducing shield gas into the outer fluid space (9), an orifice (10) in the inner skin (7) for allowing the shield gas to flow from the outer fluid space (9) into the inner fluid space (11) and an outlet pipe (12) for allowing the shield gas out of the inner fluid space (11).

7. An apparatus as claimed in claim 1 or 6, further comprising pressure control means which in use control the pressure in the inner and outer fluid space (11, 9) such that the pressure in the inner fluid space (11) is higher than the ambient pressure and the pressure in the outer fluid space (9) is higher than in the inner fluid space (11).

8. An apparatus as claimed in claim 2, wherein at least two clamps (104, 105, 106, 107) are mounted on said support frame (102), one of said clamps (104) being adapted to grip a lower tubular (110) and the other of said clamps (106) being adapted to grip an upper tubular (111), and means (108, 109) are provided for displacing one of said clamps (106) relative to the other (104) so that said tubulars (110, 111) can be urged towards one another.

9. An apparatus as claimed in claim 8, further comprising a packer (142) which in use is inserted into the interior of the tubular ends that are bonded by the apparatus, which packer comprises an elongate mandrel (143) having a resilient packer element (144, 145) adjacent each end thereof, means (151) to enable a shield gas to be introduced into an end of said elongate mandrel (143) and to leave said elongate mandrel (143) between said resilient packer elements (144, 145), and means (149) to enable water to be introduced into said end of said elongate mandrel (143) and to leave said elongate mandrel (143) between said resilient packer elements (144, 145).








Fig 3

INTERNATIONAL SEARCH REPORT

International Application No

PCT/EP 98/05474

A. CLASSIFICATION OF SUBJECT MATTER
IPC 6 B23K13/02 B23K9/00

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 6 B23K

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X Y	US 3 581 042 A (PILIA) 25 May 1971 see column 2, last paragraph - column 3, paragraph 1; figure	1,2 3,7,8
Y	US 4 139 758 A (PINFOLD) 13 February 1979 see column 5, line 23 - column 6, line 13; figure	3,7
Y	C R YEMINGTON: "Underwater NDE beyond diver depths" WELDING JOURNAL, vol. 69, no. 8, August 1990, pages 63-65, XP000140428 Miami (USA) see figure	8

☐ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents :

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (see specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"&" document member of the same patent family

Date of the actual completion of the international search

8 January 1999

Date of mailing of the international search report

14/01/1999

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Herbreteau, D

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No
PCT/EP 98/05474

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 3581042 A	25-05-1971	NONE	
US 4139758 A	13-02-1979	AU 1853376 A	20-04-1978
		AU 510031 B	05-06-1980
		AU 2109277 A	13-07-1978
		BR 7606804 A	30-08-1977
		BR 7700175 A	06-09-1977
		CA 1067159 A	27-11-1979
		DK 9677 A	13-07-1977
		DK 453776 A	11-04-1977
		EG 13307 A	31-03-1982
		FR 2327022 A	06-05-1977
		FR 2337606 A	05-08-1977
		IE 44577 B	13-01-1982
		IN 146110 A	24-02-1979
		JP 52151649 A	16-12-1977
		JP 52084137 A	13-07-1977
		NL 7611234 A	13-04-1977
		NL 7700275 A	14-07-1977
		OA 5503 A	30-04-1981
		OA 5543 A	30-04-1981



(12)

(51) Int. Cl.⁷: **B23K 13/02, B23K 9/00**

(86) International application number:
PCT/EP98/05474

(87) International publication number:
WO 99/08827 (25.02.1999 Gazette 1999/08)

2596 HR Den Haag (NL)

(72) Inventors:
 • PIETRAS, Bernd-Georg
 D-30900 Wedemark (DE)
 • JAHN, Michael
 D-29313 Hambühren (DE)

D-29313 Hambühren (DE)

(54) APPARATUS FOR AMORPHOUS BONDING OF TUBULARS

(87) This international application for which the EPO is a designated office has not been republished by the EPO according to article 158(1) EPC.

Cette demande internationale pour laquelle l'OEB est office désigné n'a pas été republiée par l'OEB en vertu de l'article 158(1) CBE.

Diese internationale Anmeldung, für die das EPA Bestimmungsamt ist, würde, gemäß Artikel 158(1) EPÜ, vom EPA nicht wieder veröffentlicht.

UN 1007